



Electro-Science Laboratories, Inc.

416 East Church Road • King of Prussia, PA 19406-2625, U.S.A
610-272-8000 • Fax: 610-272-6759 • www.ElectroScience.com • Sales@ElectroScience.com

GOLD METALLO-ORGANIC CONDUCTOR

8081-A

ESL 8081-A is a thin printing metallo-organic gold that produces a fired conductive film of less than one-micrometer in thickness. It can be used for non-migrating terminations for thick film resistors and is economical because of its high coverage. It is not recommended for wire bonding or soldering because of its thinness. This conductor contains a precious metal composition that decomposes with heat at temperatures above 300°C. At temperatures near 600°C, a "thin" film with good adhesion to the substrate is formed. By printing this conductor to the exact pattern desired, it can be used for many conductive purposes in which direct wire bonding or soldering is not required.

PASTE DATA

RHEOLOGY:	Thixotropic, screen printable paste
VISCOSITY: (Brookfield RVT, ABZ spindle, 10 rpm, 25.5°C±0.5°C)	50±10 Pa·s
SHELF LIFE: (25°C)	6 months

PROCESSING

SCREEN MESH/EMULSION:	200-325 mesh/25-33 μm
LEVELING TIME: (25°C)	5-10 minutes
DRYING: (125°C)	10-15 minutes
FIRING RANGE:	625°C-850°C
OPTIMUM:	850°C
RATE OF ASCENT/DESCENT:	60°C-100°C/minute
SUBSTRATE FOR CALIBRATION:	96% alumina
THINNER:	ESL 413

8081-A 9907-G

ESL Affiliates

Japan: ESL-Nippon Company, Ltd. • Sukegawa Bldg. • 6th floor • 3-4 Yanagibashi 1-chome • Taito-ku • Tokyo 111, Japan • Tel: (011-81)-3-3864-8521 • Fax: (011-81)-3-3864-9270
NipponSales@ESLNippon.com

China: Shanghai Agmet Electro-Science Laboratory Ltd. • Second Floor Bldg. 12A1 • #223 North Fe Te Road • Waigaoqiao Free Trade Zone • Shanghai, China
Tel: (011-86)-21-5866-0497 • Fax: (011-86)-21-5866-0497 • ShanghaiSales@ShanghaiESL.com

Europe: Agmet, Ltd. • 8 Commercial Road • Reading, Berkshire, England RG2 0QZ • Tel: (011-44)-118-987-3139 • Fax: (011-44)-118-986-7331 • Sales@ESLEurope.co.uk

See Caution and Disclaimer on other side.

TYPICAL PROPERTIES

FIRED THICKNESS: < 1 μm
RESISTIVITY: < 400 $\text{m}\Omega/\text{sq.}$

NOTES:

1. Adequate air flow and ventilation to remove the burn-off products is essential or unpleasant odors may accumulate.
2. Thinners are not normally required. ESL 413 may be used sparingly. For screen cleaning, Xylol, isopropyl alcohol, or acetone may be used.

8081-A 9907-G

CAUTION: Proper industrial safety precautions should be exercised in using these products. Use with adequate ventilation. Avoid prolonged contact with skin or inhalation of any vapors emitted during use or heating of these compositions. The use of safety eye goggles, gloves or hand protection creams is recommended. Wash hands or skin thoroughly with soap and water after using these products. Do not eat or smoke in areas where these materials are used. Refer to appropriate MSDS sheet.

DISCLAIMER: The product information and recommendations contained herein are based on data obtained by tests we believe to be accurate, but the accuracy and completeness thereof is not guaranteed. No warranty is expressed or implied regarding the accuracy of these data, the results obtained from the use hereof, or that any such use will not infringe any patent. Electro-Science assumes no liability for any injury, loss, or damage, direct or consequential arising out of its use by others. This information is furnished upon the condition that the person receiving it shall make their own tests to determine the suitability thereof for their particular use, before using it. User assumes all risk and liability whatsoever in connection with their intended use. Electro-Science's only obligation shall be to replace such quantity of the product proved defective.
